INDEX

Absorbent, 3-9, 3-10
Adobe blasting, 5-14
Aggregate, 5-24—5-25
Airblast, 7-1—7-4
Air waves, 2-1
Aluminized slurry, 3-19
Ammonia:
  dynamite, 3-10, 3-11, 3-12—3-13
  gelatin (special, extra), 3-14, 3-15, 3-16
Ammonium:
  nitrate, 3-9, 3-10, 3-12, 3-13
  nitrate-fuel oil (ANFO), 3-16
Antacid, 3-7, 3-9, 3-10
Attenuation, 2-3

Bedding, 6-9
Bench blasting, 5-4—5-12
Black powder, 3-9, 3-20—3-21
Blast-fractured zone, 2-2, 2-3
Blasting:
  agents (nitrocarbonitrates), 3-6—3-18
  cap, 3-21—3-24
  coefficient, 2-4, 6-4
  damage, 2-1, 7-1—7-18
  gelatin, 3-13, 3-14, 3-15
Blast records, 8-3—8-4, 8-5—8-6
Blockholing, 5-24
Booster, 3-19
Bulk strength, 3-1
Burden, 5-1, 5-4

C-3, 3-20
C-4, 3-20
Calcium carbonate, 3-9
Cap and fuse, 3-22, 3-23
Carbon monoxide, 3-7
Cartridge:
  count, 3-2, 3-3
  strength, 3-1—3-2, 3-3, 3-4
Cavities, 6-14—6-15
Chalk, 3-9
Characteristic impedance, 6-2—6-4
Charcoal, 3-9
Charge diameter, 3-4—3-5
Chipping, 4-1
Churn drills, 4-8, 4-11
Combustibles, 3-9
Composition B, 3-20
Compressional wave, 2-3
Compressive strength, 2-3, 2-4, 6-4
Confined velocity, 3-5
Conical bit, 4-1
Contracts, 8-1—8-7
Controlled blasting, 5-15
Coyote blasting, 5-12—5-13, 5-24, 5-26
Cratering, 5-13, 7-17
Crawler drill, 4-11, 4-12
Critical diameter, 3-5
Crushed zone, 2-2, 2-3
Crushing, 4-1
Cushion blasting, 5-21
Cyclotrimethylenetrinitramine (RDX), 3-20

Decked charges, 3-23, 5-4, 7-16
Decoupled charges, 2-3, 6-14
Deflagration, 3-1
Degree of confinement, 3-4, 3-22

Delay:
  electric blasting cap, 3-21—3-22
  patterns, 5-3
Density of explosives, 3-4, 3-5
Detonating fuse, 3-21, 3-22—3-24
Detonation, 3-1
  pressure, 3-5—3-7
  velocity, 3-1, 3-4—3-5, 3-6
Detonator, 3-21—3-24
Diamond bit, 4-4—4-5, 4-7
Dipping strata, 6-14
Displacement seismograph, 7-11—7-12
Ditching dynamite, 3-10
Down line, 3-23
Down-the-hole drill, 4-8, 4-14
Drag bit, 4-5
Drifters, 4-8
Drill bits, 4-1, 4-4—4-8
Drill systems, 4-1, 4-4
Dry blasting agents, 3-17—3-18
Dynamite, 3-10—3-13

Elastic waves, 2-1
Electric blasting cap, 3-21—3-22, 3-23
Ethylene glycol dinitrate, 3-9
Explosion cavity, 2-2
Explosive, 2-1, 3-1
  base, 3-7, 3-9
  charge distribution, 5-11, 5-12
Extra dynamite, 3-10, 3-11, 3-12—3-13

Fabric, 6-4, 6-7, 6-11—6-12
Fault breccia, 6-9—6-11
Faults, 6-9
Ferrosilicon, 3-16
Flyrock, 7-17—7-18
Fragmentation, 2-2, 5-24
Free face, 2-3
Fuel oil, 3-9
Fume class, 3-7

Gelatins, 3-13—3-16
Grade, 3-13
Ground:
  coal, 3-9
  vibrations, 7-5—7-16
Groundwater, 6-16
Guar gum, 3-19
Guide holes, 5-20

Hammer:
  bits, 4-8—4-10
  drills, 4-8—4-15
Hemispherical bit, 4-1
High-density ammonia dynamite, 3-10, 3-11, 3-12
High explosive, 3-1
High velocity gelatin, 3-15
Hole array, 5-1—5-4
Hoop stresses, 2-3
Horizontal presplitting, 5-20

Inclined blastholes, 5-5
Ingredients of explosives, 3-7, 3-9, 3-10

Jackhammers, 4-8, 4-9, 5-23
Jet-piercing, 4-1

INDEX (Cont'd)

Jetty stone, 5-24
Joint coating, 6-7, 6-8
Jointing, 6-4, 6-7
Joint orientation, 6-7, 6-8—6-9

Kieselguhr (diatomite), 3-2, 3-9

Lampblack, 3-9
Lead azide, 3-9
Lifter, 5-6, 5-8
Line drilling, 5-21, 5-22—5-23
Liquid oxygen explosive (LOX), 3-9
Low-density ammonia dynamite, 3-11, 3-12—3-13
Low-energy detonating cord (LEDC), 3-24
Low explosive, 3-1

Mechanics of drilling, 4-1, 4-4
Mercury fulminate, 3-9
Metallic powder, 3-9
Microphone, 7-4
Millisecond:
  connector, 3-23—3-24
  delay, 3-22, 7-13
Mudcapping, 5-24

Nitrocellulose (guncotton), 3-9
Nitrogen oxide, 3-7
Nitroglycerin, 3-9
Nitrostarch, 3-9

Oil well explosive, 3-13
Oxygen carrier, 3-7

Paraffin, 3-9
Particle size, 3-4
Peak particle velocity, 7-5
Peak pressure, 2-1
Pentaerythritol tetranitrate (PETN), 3-9, 3-21
Pentolite, 3-20
Percussive drills, 4-8—4-14
Permissible explosive, 3-20
Piezoelectric pressure gage, 7-4
Plug bits, 4-4
Pneumatic loading, 3-18
Porosity, 6-4, 6-6
Powder factor, 5-4, 6-4, 6-5
Power augers, 4-5, 4-8
Presplitting, 5-15—5-19, 6-7, 6-12, 7-16
  corners, 5-20, 5-21
Prill, 3-17
Primary waves, 2-1
Primer, 3-16, 3-21
Prismatic bit, 4-1
Pyramidal bit, 4-1

Quarrying, 5-23—5-26, 6-1, 6-12

RDX (cyclotrimethylenetrinitramine), 3-20
Riprap, 5-24
Rock fills, 5-25—5-26
Roller bit, 4-4, 4-6
Rotary drills, 4-3—4-8, 4-11, 4-14—4-15
Rotary-percussive drill, 4-11, 4-14—4-15

Safety, 1-1—1-2
Scaling, 5-15
  factor, 7-4
Seismic:
  explosive, 3-15
  velocity, 6-1—6-2
  zone, 2-2
Seismograph, 7-12
Semigelatin, 3-14, 3-16
Sensitivity, 3-7
Shaped charges, 3-20
Shear waves, 2-1
Slow delay, 3-22
Slurry:
  blasting agent, 3-19
  boosting, 3-19
Snake hole, 5-6, 5-7, 5-8
Sodium:
  chloride, 3-9
  nitrate, 3-9
Spacing, 5-1
Spalling, 2-3—2-4, 4-1, 7-17
Stemming, 7-1
Stopers, 4-8
Straight:
  gelatin, 3-13, 3-14, 3-15
  nitroglycerin dynamite, 3-10, 3-11, 3-12
Strengths of explosives, 3-1—3-4
Subdrilling, 5-11—5-12
Sulfur, 3-9, 3-12

Tensile strength, 2-3, 2-4, 6-4
Tensional wave, 2-3
Tetranitro-diglycerin, 3-9
Trapezoidal array, 5-4—5-5
Trenching, 5-13
Trinitrotoluene (TNT), 3-9, 3-20
Trunk line, 3-23

Unconfined velocity, 3-4
Underwater blasting, 5-13—5-14

Velocity seismograph, 7-11—7-12
Vibratory drills, 4-8

Wagon drill, 4-8, 4-11
Water:
  gels, 3-18
  resistance, 3-1, 3-7
Weathering coefficient, 6-15
Weight strength, 3-1—3-4
Wood pulp, 3-9

Zinc oxide, 3-9